



* Product Name: ICHOR 9704

- Siloxane UV Curing Resin

- **Properties:** Low Curl, High Hardness /Low viscosity/Abrasion and mar-resistance /Thermal resistance/
Solvent, chemical resistance
- **Application:** Optical coating/ UV Hard coating

* Properties Data

ITEM	SPECIFICATION
Solid Content (wt. %)	60% ± 0.5 (150, 30min)
Viscosity (cps)	Below 10,000 /25°C/62s, 6 rpm
Specific Gravity	1.35± 0.2 /25°C
Appearance & Color	Light Yellow Color
Storage/Shelf Life	Storage: 0 ~ 20°C, Shelf Life: 5 months when unopened, 1 month after opening

- Instructions for use

- * Recommendation of blending with appropriate organic Urethane acrylate or UV curable monomers for functionality coatings.
- * Photo initiator dosage: 1 ~ 5%
- * Coating area should be clean, dust-free. If necessary, parts should be washed or clean with Isopropyl alcohol