



* Product Name: ICHOR 9710A

- **Siloxane UV Curing Resin (Cationic photo polymerization and Heat curing type)**

- **Properties:** Flexibility /Low Curl /Abrasion and mar-resistance/Thermal resistance/

Solvent, chemical resistance

- **Application:** Optical coating/ UV & Heat curing type

* Properties Data

| ITEM | SPECIFICATION |
|-----------------------|---|
| Solid Content (wt. %) | 60% ± 0.5 (150, 30min) |
| Viscosity(cps) | Below 10,000 /25°C/62s, 6 rpm |
| Specific Gravity | 1.20± 0.2 /25°C |
| Appearance & Color | Light Yellow Color |
| Storage/Shelf Life | Storage: 0 ~ 10°C, Shelf Life; 5 months when unopened, 1 month after opening |

- Instructions for use

* Recommend of blending with cycloaliphatic epoxy resin or Oxetane for flexibility and functionality coatings.

* Cationic or Radical Photo initiator dosage: 1 ~ 5%

* Coating area should be clean, dust-free. If necessary, parts should be washed or clean with Isopropyl alcohol