



Head office: Samwhan Bldg., 88 Yulgok-ro, Jongno-gu, Seoul 110-310, South Korea TEL: 82-2-3210-5400, FAX: 82-2-3673-5903

R&D Center: 32-27, Wonnamsandan 1-gil, Wommanam-myeon, Eumseong-gun, Chungcheonbuk-do, 369-863, South Korea TEL: 82-43-873-8216, FAX: 82-2-873-7220

Homepage: [www.Chemtech-int.com](http://www.Chemtech-int.com)

## \* Product Name: ICHOR 9710HAF

- Bendable UV-curing coating solution for CPI (Applicable field: substrates of CPI and bendable plastics for display and smartphone)
- Properties: Abrasion and Mar-resistance, Low Curl, Optical Property, Slip & Easy Clean

### \* Coating conditions (drying, curing, post aging)

- Drying conditions: 100°C, 1min / UV curing conditions: 1500mJ/Cm<sup>2</sup>

### \* Properties Data

ITEM		SPECIFICATION
Solid Content (wt. %)		40% ± 0.5 (150, 30min)
Viscosity(cps)		Below 200/25°C. 61s, 60RPM
Specific Gravity		Below 1.0± 0.3 /25°C.
Appearance & Color		Clear ~ Light Yellow Color
Storage/Shelf Life		Storage: 0 ~ 10°C, Shelf Life; 5 months when unopened, 1 month after opening
Curing Condition		After drying at 100°C for 1 minute, UV curing(1500 mJ / cm <sup>2</sup> )
Coating Substrate		CPI(KOLON), 50 µm
Bar Number		#24
Coating Thickness		10 µm
INSPECTION ITEM		SPECIFICATION
Properties	Pencil Hardness	4H(1kg) / 5H(750g)
	Adhesion	100/100/3M Magic Tape
	Bending Test	3.5mm, No Crack
	Curl	Below 20mm
	Scratch Resistance	No Scratch #0000 Steel Wool, 1.5kg Load/1000 PASS(10 µm)
	Chemical Resistance	Alcohol, 25 °C, 4hr
	Hot Water Resistance	PASS, 90~ 95 °C, 60min
	Transmittance	Above 90% , UV Spectrometer

\* Pencil Hardness; KS M ISO 15184:2013, Adhesion: D 3359 방법에 의거하여 측정됨.

\* 상기 DATA는 ㈜ 캠펙인터내셔널의 자체 성능 평가 기준에 의해 분석된 수치이며, 적용되는 모든 환경에서 절대적인 물질 특성치를 나타내는 것은 아닙니다.