



Head office: Samwhan Bldg., 88 Yulgok-ro, Jongno-gu, Seoul 110-310, South Korea TEL: 82-2-3210-5400, FAX: 82-2-3673-5903

R&D Center: 32-27, Wonnamsandan 1-gil, Wommanam-myeon, Eumseong-gun, Chungcheonbuk-do, 369-863, South Korea TEL: 82-43-873-8216, FAX: 82-2-873-7220

Homepage: [www.Chemtech-int.com](http://www.Chemtech-int.com)

## \* Product Name: ICHOR 9754G15

- 고경도 UV 경화형 AG하드코팅액(적용 분야: PET, PMMA 기재의 광학용 코팅/하드코팅)

- Properties: Anti-Glare, Low Curl, High Hardness, Abrasion and Mar-resistance, Slip & Easy Clean

\* 코팅 조건(건조, 경화, 숙성)

- 건조 조건: 100°C, 1min /UV경화조건 300mJ/Cm<sup>2</sup>

- 숙성 작업: Roll(85mm)에 코팅면 반대방향으로 감아, 55°C, 24hr 동안 Aging 작업(경도 향상 및 Curl 감소)

## \* 물성 Data

ITEM	SPECIFICATION
	ICHOR 9754G15
Solid Content (wt. %)	45.5% ± 0.5 (150, 30min)
Viscosity(cps)	200 이하/25°C. 61s, 60RPM
Specific Gravity	1± 0.3 이하/25°C.
Appearance & Color	Clear ~ Light Yellow Color
Storage/Shelf Life	Storage: 0 ~ 5°C, Shelf Life: 미개봉시 3개월, 개봉 후 1개월

## \* Haze 5%, AG coating 배합비

- 배합비 (코팅액 : 비드 = 75.5 : 1.000)

- Ex) 코팅액(50.000 g) : 비드(0.662 g) = 75.5: 1



# Chemtech International Co., Ltd.

Head office: Samwhan Bldg., 88 Yulgok-ro, Jongno-gu, Seoul 110-310, South Korea TEL: 82-2-3210-5400, FAX: 82-2-3673-5903

R&D Center: 32-27, Wonnamsandan 1-gil, Wommanam-myeon, Eumseong-gun, Chungcheonbuk-do, 369-863, South Korea TEL: 82-43-873-8216, FAX: 82-2-873-7220

Homepage: [www.Chemtech-int.com](http://www.Chemtech-int.com)

## \* 9754G5Haze 15%, 물성 data

ITEM	SPECIFICATION	
	ICHOR 9754G15	
Mix proportion (wt. %)	코팅액 : 비드 = 75.5 : 1	
Solid Content (wt. %)	45.5% ± 0.5 (150, 30min)	
Viscosity(cps)	200 이하/25°C. 61s, 60RPM	
Specific Gravity	1± 0.3 이하/25°C.	
Appearance & Color	Clear ~ Light Yellow Color	
Storage/Shelf Life	Storage: 0 ~ 5°C, Shelf Life: 미개봉시 3개월, 개봉 후 1개월	
Curing Condition	100도, 1분 건조 후, UV 경화(300mJ/Cm <sup>2</sup> )	
Coating Substrate	PET(U43R 코오통), 188 µm	
Aging	85mm 봉에 코팅 반대편으로 감아, 55°C, 12 ~ 24hr 동안 Aging 작업	
Bar Number	#10	
Coating Thickness	10 µm	
INSPECTION ITEM		SPECIFICATION
Properties	Pencil Hardness	3H(1kg)
	Adhesion	100/100/3M Magic Tape
	Bending Test	30mm, No Crack
	Curl	20mm 이하
	Chemical Resistance	Alcohol, 25 °C, 4hr
	Hot Water Resistance	PASS, 90~ 95 °C, 60min
	투과율	80% , UV Spectrometer

\* Pencil Hardness; KS M ISO 15184:2013, Adhesion: D 3359 방법에 의거하여 측정됨.

\* 상기 DATA는 (주) 캬텍인터내셔널의 자체 성능 평가 기준에 의해 분석된 수치이며, 적용되는 모든 환경에서 절대적인 물질 특성치를 나타내는 것은 아닙니다.